

FOR FURTHER TRAN




AD A 054670

Research and Development Technical Report
Report ECOM-76-0872-5

III-V HETEROJUNCTION STRUCTURES FOR LONG-WAVELENGTH INJECTION LASER

C. J. Nuese, G. H. Olsen, R. E. Enstrom,
and M. Ettenberg
RCA Laboratories
Princeton, New Jersey 08540



AD NO. _____
DDC FILE COPY

MAY 1978

Fifth Interim Quarterly Report for Period 16 August 1977
to 15 November 1977

Approved for public release; distribution unlimited.

Prepared for
ECOM

US ARMY ELECTRONICS COMMAND FORT MONMOUTH, NEW JERSEY 07703

Disclaimers

The findings in this report are not to be construed as an official Department of the Army position, unless so designated by other authorized documents.

The citation of trade names and names of manufacturers in this report is not to be construed as official Government endorsement or approval of commercial products or services referenced herein.

Disposition

Destroy this report when it is no longer needed. Do not return it to the originator.

⑨ Quarterly rept. no. 5 (Interim), 16 Aug
15 Nov 77,

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

19 REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM	
1. REPORT NUMBER ⑮ ECOM-76-0872-5	2. GOVT ACCESSION NO.	3. RECIPIENT'S CATALOG NUMBER	
4. TITLE (and Subtitle) ⑥ III-V HETEROJUNCTION STRUCTURES FOR LONG- WAVELENGTH INJECTION LASER.		5. TYPE OF REPORT & PERIOD COVERED Interim Quarterly Rpt. No. 5 8-16-77 to 11-15-77	
		6. PERFORMING ORG. REPORT NUMBER ⑭ PRRL-78-CR-22	
7. AUTHOR(s) ⑩ C.J. Nuese, G.H. Olsen, R.E. Enstrom M. Ettenberg		⑮ CONTRACT OR GRANT NUMBER(s) DAAB07-76-C-0872, ARPA Order -3137	
9. PERFORMING ORGANIZATION NAME AND ADDRESS RCA Laboratories ✓ Princeton, New Jersey 08540		10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS ARPA AO 3137 6D10 001	
11. CONTROLLING OFFICE NAME AND ADDRESS Advanced Research Projects Agency		12. REPORT DATE ⑪ May 1978	
		13. NUMBER OF PAGES 15	
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office) US Army Electronics Research & Development Command Attn: DELNV-L Fort Monmouth, NJ 07703		15. SECURITY CLASS. (of this report) Unclassified	
16. DISTRIBUTION STATEMENT (of this Report) Distribution unlimited; approved for public release.			
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)			
18. SUPPLEMENTARY NOTES			
19. KEY WORDS (Continue on reverse side if necessary and identify by block number) Injection Lasers, Quaternary Devices, Vapor Epitaxy, Heterojunction, Etching Solution			
20. ABSTRACT (Continue on reverse side if necessary and identify by block number) (U) Several double heterostructure injection lasers were fabricated from vapor-grown InGaAs P/InP. Laser wavelength was 1.4 μm . The lowest threshold current density observed was 2385 A/cm ² . The etching characteristics of bromine-methanol-phosphoric acid solutions on InP were tabulated.			

DD FORM 1 JAN 73 1473

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

299 \$\$\$

Gu

TABLE OF CONTENTS

Section	Page
I. OBJECTIVE	1
II. PROGRESS	2
A. 1.4- μ m Wavelength Lasers	2
B. 1.1- μ m Wavelength Lasers	5
III. PLANS FOR NEXT QUARTER	7
IV. FINANCIAL STATUS	8
V. DISTRIBUTION	9

ACCESSION for		
NTIS	White Section	<input checked="" type="checkbox"/>
DGC	Buff Section	<input type="checkbox"/>
UNANNOUNCED		<input type="checkbox"/>
JUSTIFICATION		
BY		
DISTRIBUTION/AVAILABILITY CODES		
Dist.	Avail.	SPECIAL
A		

SECTION I

OBJECTIVE

The long-term objective of our research program is to develop high-quality heterojunction lasers (pulsed and cw) and photodiodes capable of operating at any desired wavelength primarily between 0.92 and at least 1.7 μm , although wavelengths in excess of 2.0 μm should be feasible. In this second phase of our program, the use of vapor-grown quaternary alloys will be evaluated in heteroepitaxial device structures. These structures are comprised of (In, Ga) (As,P) and InP layers deposited primarily onto InP substrates.

SECTION II

PROGRESS

In the first quarter of our quaternary InGaAsP program, we calibrated and optimized the various flow parameters essential to the vapor deposition of this material; we also characterized InP substrates presently available, and established a reasonable chemical polishing technique for preparing substrates for subsequent vapor deposition. Details of these efforts were reported in Quarterly Report No. 4.

In the present quarter, we began the preparation of double-heterojunction laser structures of InGaAsP/InP. Two different reactors were employed for these devices: one for structures with emission wavelengths between 1.1 and 1.2 μm , and the other for structures with wavelengths near 1.4 μm . Progress with both structures has been very rapid; room-temperature pulsed lasers have been consistently obtained, with threshold currents as low as 2400 A/cm^2 at 1.38 μm , and 3830 A/cm^2 at 1.12 μm . Details of these structures are given below.

A. 1.4- μm WAVELENGTH LASERS

The InGaAsP alloys prepared for heterojunction structures at 1.4 μm have an energy bandgap of approximately 0.83 eV. The composition used to achieve this value, while matching the InP lattice parameter (5.869 \AA), is about $\text{In}_{0.69}\text{Ga}_{0.31}\text{As}_{0.71}\text{P}_{0.29}$. Comparison of measurements for energy bandgap (by optical absorption), alloy composition (by electron microprobe analysis), and lattice parameter (by x-ray diffraction) established the general validity of the previously-published set of curves relating E_g , x , and a_0 for the regime around 0.8 eV. Furthermore, the reproducibility of vapor-grown alloy composition (within about 1%) was established by the virtual agreement of E_g , x , and a_0 on two successive runs.

Next, a series of double-heterojunction lasers was prepared consisting of a homoepitaxial vapor-grown layer of n-type InP on the n-type InP substrate, followed by an n-type $\text{In}_{0.69}\text{Ga}_{0.31}\text{As}_{0.71}\text{P}_{0.29}$ active layer, a p-type InP confining layer and a p-type $\text{In}_{0.69}\text{Ga}_{0.31}\text{As}_{0.71}\text{P}_{0.29}$ capping layer to facilitate contacting. The electrical properties, as determined from Hall-effect measurement, of these layers are given in Table I.

TABLE I. ELECTRICAL PROPERTIES OF LAYERS IN
LONG-WAVELENGTH LASER STRUCTURES

<u>Layer</u>	<u>Alloy Composition</u>	<u>Doping Type</u>	<u>Carrier Concentration (cm⁻³)</u>	<u>Mobility (cm²/V-s)</u>
1	InP	n (S)	1.6×10^{17}	2,770
2	InGaAsP	n (S)	4.4×10^{17}	3,180
3	InP	p (Zn)	1.1×10^{18}	57
4	InGaAsP	p (Zn)	6.1×10^{18}	49

The preliminary characteristics of lasers fabricated from these double-heterojunction structures are summarized in Table II. Here, room-temperature threshold current density values for six of our last seven runs are seen to be below 7000 A/cm^2 with a minimum value of 2400 A/cm^2 . These current densities are nearly low enough to achieve cw operation at room temperature.

A plot of the threshold current densities in Table II versus the laser cavity thickness (for those samples where the thickness has thus far been determined) shows that J_{th} decreases monotonically with cavity thickness. Accordingly, future samples will be prepared with cavity thickness near or below $0.12 \text{ }\mu\text{m}$, so that still lower threshold currents can be obtained. We also should add that the differential quantum efficiency value measured on a few of these lasers is on the order of 30%, which is typical of that obtained from our ternary InGaAs/InGaP lasers developed earlier in this program. Measurement of the emission wavelength has been initiated, and for sample 2306 - 1.5" it is $1.38 \text{ }\mu\text{m}$. The other samples are expected to be close to this value.

Our investigation of InP polishing etches has continued. In the previous report, results using a bromine-methanol solution were given. This solution is rapid and effectively removes work damage, however the resulting surface is not quite as smooth as desired. Accordingly, bromine-methanol solutions containing phosphoric acid have been recently investigated. The results for this etchant are given in Table III. Solutions (3) and (5) appear to yield very good surfaces, although the polishing rate is somewhat slower than that of

TABLE II. PROPERTIES OF InGaAsP/InP 1.4- μ m DH LASERS

<u>Sample</u>	<u>t_{cav} (μm)*</u>	<u>J_{th} (A/cm²)</u>
2292 - 2"	-	2385
-1.5"	0.15	2630
2298 - 2"	0.25	5810
-1.5"	-	6590
2299 - 2"	-	6460
-1.5"	0.17	7675
2300	NO LASING, BAD In	
2340 - 2"	0.27	6235
-1.5"	-	4310
2306 - 2"	-	4170
-1.5"	0.20	3230
2307 - 2"	0.22	4030
-1.5:	0.12	2390

*From SEM

TABLE III. ETCHING CHARACTERISTICS OF BROMINE-METHANOL-PHOSPHORIC SOLUTIONS ON InP

<u>No.</u>	<u>Bromine, Phosphoric Acid Concentrations in 100 ml of Methanol</u>			<u>Etching Rate (μm/min)</u>	<u>Surface Appearance</u>
	<u>Br</u>	-	<u>H₃PO₄</u>		
(1)	1 ml		40 ml	0.44	Good
(2)	2 ml		80 ml	0.25	Good (sol. loses Br upon standing)
(3)	2 ml		40 ml	0.69	Very Good
(4)	3 ml		40 ml	2.17	Large Surface Defects
(5)	3 ml		60 ml	0.95	Very Good

the standard 1% bromine-methanol solution. It also appears that different solutions might be required for InP substrates originating from different vendors, so our work on polishing techniques is expected to continue.

B. 1.1- μ m WAVELENGTH LASERS

For this wavelength range, the desired lattice-matching quaternary alloy is $\text{In}_{0.84}\text{Ga}_{0.16}\text{As}_{0.31}\text{P}_{0.69}$. During the past quarter, double-heterojunction lasers of InGaAsP/InP have been grown for emission near 1.1 μm . To date, several of these structures have been found to be capable of room-temperature lasing, with the lowest threshold current density from them being 3800 A/cm^2 . Differential quantum efficiencies of a few of these samples are about 30%, like those of our long-wavelength quaternary lasers described above. For one double-heterojunction structure, a portion of the wafer was fabricated into oxide-defined stripe-contact lasers, which were found to have threshold currents as low as 375 mA at room temperature (See Fig. 1). Devices of this type are presently being evaluated for the purpose of attaining cw operation near room temperature.




Figure 1. Relative light output vs input current for a stripe-contacted 1.1- μm DH laser.

We should note that our photoluminescence facility has recently been modified to allow its use to wavelengths as long as 1.8 μm . This required the addition of a high-power argon laser (2-W cw maximum) and a Ge photodiode. Photoluminescence evaluation of the InGaAsP layers is used daily as a means of providing information on alloy composition (from the photoluminescence wavelength coupled with x-ray measurements of the lattice constant) and on crystal quality (from the relative photoluminescence intensity under standardized measurement conditions).

SECTION III

PLANS FOR NEXT QUARTER

1. Double-heterojunction laser structures of InGaAsP/InP will continue to be grown for emission near 1.1 μm and 1.4 μm at room temperature. Emphasis will be on reducing the laser threshold further to allow the devices to reach cw operation at room temperature.
2. A study of photodiode structures at both wavelengths will begin after cw operation is attained.

SECTION IV
FINANCIAL STATUS

As of 30 Nov. 1977, \$229,000 has been charged to this ARPA contract in support of our heterojunction program.